

LSHN



Heavy Wall Adhesive-Lined Cross-linked Polyolefin Heat Shrink Tubing

Heavy wall adhesive-lined heat shrink tubing provides maximum reliability for insulating and protecting cable joints and terminations

Features and Application

3:1 shrink ratio, not flame-retardant

Withstands severe mechanical requirements of U.R.D., submersible and direct burial installations

High impact, abrasion, corrosion and chemical resistance

Rated for 1kv, 90°C application

Thermoplastic adhesive liner provides complete environmental protection and installation

Tubing without adhesive is available upon request

Standard color is black, other color is available upon request

Continuous operating temperature: -45°C-110°C

Shrinking temperature: 125°C

Technical Data

Property	Test method	Standard performance
Tensile strength(MPa)	ASTMD 2671	≥12
Elongation(%)	ASTMD 2671	≥300
Tensile strength after aging(MPa)	UL224 158°C*168h	≥8,4
Elongation after aging (%)	UL224 158°C*168h	≥200
Dielectric strength(kV/mm)	IEC 60243	≥15
Volume resistivity(Ω.cm)	IEC 60093	≥10 ¹⁴
Longitudinal Shrink Ratio (%)	UL224	≤ ± 10%

Adhesive

Property	Test method	Standard Performance
Water Absorption	ASTM D 570	<0,2%
Softening Point(°C)	ASTM E 28	95
Peel strength (PE)	ASTMD 1000	120N/25mm
Peel strength (AL)	ASTMD 1000	80N/25mm

TECHNICAL DATA SHEET

Revision Number. 1

Last Edited 4. juli 2023

Dimensions

Size	As Supplied (mm)	After Recovery (mm)				Standard Package
mm	Internal Diameter (mm)	Internal Diameter (mm)	Jacket Thickness (mm)	Adhesive Thickness (mm)	Total Wall Thickness (mm)	m/pc
8.0/2.0	≥8.0	≤2.0	1.80±0.30	0.55±0.20	2.35±0.35	1.22
9.0/3.0	≥9.0	≤3.0	2.00±0.30	0.55±0.20	2.55±0.40	1.22
13.0/4.0	≥13.0	≤4.0	2.30±0.30	0.55±0.20	2.85±0.40	1.22
16.0/5.0	≥16.0	≤5.0	2.30±0.30	0.60±0.20	2.90±0.50	1.22
22.0/6.0	≥22.0	≤6.0	2.50±0.40	0.60±0.20	3.10±0.50	1.22
28.0/6.0	≥28.0	≤6.0	2.70±0.40	0.70±0.25	3.40±0.50	1.22
33.0/8.0	≥33.0	≤8.0	2.80±0.40	0.80±0.25	3.60±0.60	1.22
38.1/12.0	≥38.1	≤12.0	3.10±0.50	0.80±0.25	3.90±0.60	1.22
43.2/12.0	≥43.2	≤12.0	3.50±0.50	0.80±0.25	4.30±0.70	1.22
55.0/16.0	≥55.0	≤16.0	3.60±0.50	0.80±0.25	4.40±0.70	1.22
65.0/19.1	≥63.0	≤19.0	3.60±0.50	0.80±0.25	4.40±0.70	1.22
75.0/22.0	≥75.0	≤22.0	3.60±0.50	0.80±0.25	4.40±0.70	1.22
85.0/25.0	≥85.0	≤25.0	3.60±0.50	0.80±0.25	4.40±0.70	1.22
95.0/30.0	≥95.0	≤30.0	3.60±0.50	0.80±0.25	4.40±0.70	1.22
105.0/30.0	≥105.0	≤30.0	3.80±0.60	0.80±0.25	4.60±0.70	1.22
120.0/39.0	≥120.0	≤39.0	3.80±0.60	0.80±0.25	4.60±0.70	1.22
130.0/40.0	≥130.0	≤40.0	3.80±0.60	0.80±0.25	4.60±0.70	1.22
140.0/42.0	≥140.0	≤42.0	3.80±0.60	0.80±0.25	4.60±0.70	1.22
160.0/50.0	≥160.0	≤50.0	3.80±0.60	0.80±0.25	4.60±0.70	1.00
180.0/60.0	≥180.0	≤60.0	3.80±0.60	0.80±0.25	4.60±0.70	1.00
200.0/69.0	≥200.0	≤69.0	3.80±0.60	0.80±0.25	4.60±0.70	1.00
230.0/78.0	≥230.0	≤78.0	4.10±0.60	0.80±0.25	4.90±0.70	1.00